

# PRODUCT APPLICATION

## DuraGloss 30+™

Satin Sheen ▪ Interior Use ▪ 72-Hour Cure Time

SS DuraGloss 30+™ may be applied to concrete that has cured at least 14 days. For best results, apply to surfaces that have been treated with SS Harden X™ or SS Harden X SI™. Proper surface preparation and product application is essential to performance. Please read the instructions in full prior to application.

### Equipment Needed for Application

- 100% polyester microfiber pads
- SealSource® diamond-impregnated pads
- Floor burnisher with a minimum of 1,500 RPMs

### Surface Preparation

ALLOW NEW CONCRETE TO CURE FOR A MINIMUM OF 14 DAYS PRIOR TO APPLICATION.

1. Mechanically remove any surface laitance and patch or fill cracks and damaged areas. (Etching the surface with an acidic solution is not recommended. If chemical preparation is necessary, however, the surface must be neutralized with a pH-neutral cleanser prior to application to prevent surface whiting.)
2. Thoroughly clean the surface and remove any membrane-forming curing compounds, wax, sealers, oil, grease, dirt, drywall residue or other contaminants.
3. Thoroughly scrub surface to remove any remaining dirt or dust (avoid using cleaners with butoxyethanol.) Allow surface to dry completely prior to application.

### Product Application

1. Shake the material in the container before application.
2. Apply a very thin coat of SS DuraGloss 30+™ with a 100% polyester microfiber pad at a rate of 1,500 sq/ft per gallon (35 m<sup>2</sup> per liter) or more, depending on porosity of the surface. Spread material thinly and evenly to achieve a consistent, wet appearance. (A thin application may streak; a heavy coat will appear milky or cloudy.)
3. Allow surface to dry, then burnish with SealSource® diamond-impregnated pads using a floor burnisher with a minimum of 1,500 RPMs.
4. Apply a second coat. Allow to dry and burnish.

Keep surface dry for 72 hours following treatment to allow it to cure properly.

### Application in High Humidity

Apply the material as above, increasing cure time as needed to allow surface to dry between applications. Surface must remain dry for up to 96 hours or more following treatment to allow material to cure properly.

## **Product Disclaimers**

**SS DuraGloss 30+™** will not bridge or fill cracks and will not salvage honeycombed or structurally unsound surfaces.

The fast-drying and extremely durable bonding characteristics of **SS DuraGloss 30+™** will permanently bond to a variety of surfaces and is extremely difficult to remove once it has cured. It is strongly recommended that areas which could be affected by splatters, splashes, or overspray be masked and protected prior to treatment.

**DO NOT ALLOW SS DuraGloss 30+™ TO FREEZE OR TO BE STORED AT TEMPERATURES ABOVE 120° F (48° C)**