

SS KromaKrete™ System

UV-Stable Lithium Colored Hardener

EQ Credit 4: low-emitting VOC compliant materials



348 W. Center Street, Orem, UT 84057

TEL: 801.224.3800 / FAX: 801.224.3700

SALES / TECH SUPPORT: 800.305.9144

www.sealsource.com

PRODUCT DATA SHEET

SS KromaKrete™ is a non-polishable concrete-coloring system that provides superior stain resistance in addition to the benefits of a penetrating hardener/densifier. **SS KromaKrete™** penetrates the surface to bond to the substrate, protecting against abrasion and dusting. When used with **SS DuraGloss™** as recommended, the **SS KromaKrete™** system creates a durable, UV-stable surface that is easy to clean and maintain—dramatically reducing maintenance costs and downtime. The unmatched protection of the **SS KromaKrete™** system outlasts any product of its kind in the industry.

SS KromaKrete™ is designed for interior or exterior use and is available in thirteen standard, stock colors. Custom colors are available upon request.

USES

SS KromaKrete™ brings a combination of industrial durability and aesthetic value allowing it to be an excellent application for industrial uses, as well as, retail, manufacturing, etc. In addition, the superiority of the stain protection maintains a clean, stain-free environment for restaurants, grocery stores, retail stores, warehouses, etc.

ADVANTAGES

- Water/Oil Repellent
- Reduced Maintenance Costs
- Fast Cure Times
- Penetrating
- Odorless
- Increased Abrasion Resistance
- Superior Stain Resistance
- Meets and Exceeds OSHA and ADA coefficient of friction
- Interior/Exterior Application

PHYSICAL PROPERTIES

- Form: various colors, aqueous solution
- Total Solids: 23%
- Active Ingredients: 100% of total solids
- Specific Gravity: 1.09
- pH 11.5
- Flash Point: N/A
- VOC Content: < 50gms/L



- Freeze Point: 32° F (0° C)
- Abrasion Resistance: excellent
- Depth of Surface Penetration: 2-8 mm

PACKAGING

- 55 Gallon Drums-Drum containers filled by weight, volume is closely approximate.
- 5 Gallon Pails

MIXING

SS KromaKrete™ is a single component product. Mechanically stir for 5-10 minutes prior to use.

SAFETY

- Read Material Safety Data Sheet before using
- Keep out of reach of children
- Protect from freezing
- Wear safety glasses and rubber gloves
- Do not apply to soft metals
- Do not apply to glass

APPLICATION RECOMMENDATIONS

SS KromaKrete™ should be applied by a low pressure sprayer, airless sprayer or rolled on and worked in with a broom. Apply a minimum of two applications at 400 sq.ft./gallon (10 m²/liter). Allow material to dry for 1 hour in between applications

SHELF LIFE

Six months, in original, unopened factory containers under normal storage conditions of 55°-95° F.

WARRANTY

SealSource® International LLC, will refund the price of or replace, at its election, product it finds to be defective provided the product has been used properly. Except as expressly stated above, the Company makes no warranty of merchantability and no warranty of fitness for any particular purpose, nor does it make any warranty, expressed or implied, of any nature whatsoever with respect to the product or its use. In no event shall the company be liable for delay caused by defects, for loss of use, for indirect, special or consequential damages, or for any charges or expenses of any nature incurred without its written consent.